



TECHNICAL DATA SHEET

TRADE BRICKDRESSING

REVISION DATE: July 2024
(Supersedes all previous publications)

PRODUCT INFORMATION

PRODUCT DESCRIPTION

BRICKDRESSING is a clear varnish with excellent penetration to seal and enhance **interior** brick surfaces.

PRODUCT USES

To seal and enhance the colour of interior brick surfaces. For exterior brick surfaces refer to SABRE MASONRY WATER REPELLENT. Not for use on fresh cement surfaces.

TECHNICAL INFORMATION

GENERIC TYPE

Alkyd oil

FINISH

Slight sheen

VOLUME SOLIDS

35 ± 1%

SPECIFIC GRAVITY

0.90kg/litre

RECOMMENDED DFT

30 - 35 microns per coat. Two coats required.

RECOMMENDED WFT

80 - 100 microns per coat. Two coats required.

SPREAD RATE

Smooth Surface	Rough Surface
10 - 12 m ² /ℓ	7 - 9 m ² /ℓ
Surface porosity, profile, application tools and technique will affect practical spread rate	

LEAD FREE

Yes

FLASH POINT

38°C

COLOURS

Clear

PACK SIZE

500 mℓ, 1ℓ and 5ℓ

STORAGE

Store away from direct sunlight, heat and severely cold or damp conditions. Ensure that containers are properly sealed before storage.

APPLICATION DETAILS

PRIOR TO USE

Mix well using a flat paddle until homogeneous in consistency.

APPLICATION METHOD

Brush, mohair roller or airless spray.

THINNING

Mineral Turpentine

CLEANING OF EQUIPMENT

Mineral Turpentine

DRYING TIME (@ 25°C & 65% RH)

Touch dry	4 hours
Over coating	16 hours

Note: higher temperatures will accelerate the drying times (approximately halved for every 10°C increase), whilst lower temperatures will retard the drying times (approximately doubled for every 10°C decrease).

APPLICATION CONDITIONS

	MIN	MAX
Surface Temp (°C)	10 °C	40°C
Ambient Temp (°C)	10 °C	40°C
Relative Humidity	10%	85%
<i>or 4°C minimum above dew point</i>		

SUBSTRATE CONDITIONS

Substrate must be clean, dry and sound for painting.
Moisture content must be **below 5% WME**, measured using a PROTIMETER (or equally approved).

SAFETY PRECAUTIONS

Ensure good ventilation during application and curing process.
Keep out of reach from children.
In case of skin contact, wash with soap and water.
In case of eye contact rinse immediately with running water and seek medical advice if eyes are irritated.
If swallowed, do not induce vomiting and seek immediate medical attention.
Always wear the appropriate protective clothing during product handling and application.
Refer to Material Safety Data Sheet on our website for more detailed safety information

SURFACE PREPARATION

Ensure that all surfaces are dry, clean and free of oil, grease, laitance and in accordance with above **SUBSTRATE CONDITIONS**.

NEW WORK

Dust off the surface. Apply directly.

PREVIOUSLY PAINTED SURFACES

BAD CONDITION

Sand down with 100 grit sandpaper or by mechanical means. SABRE PAINT REMOVER may be used in areas where build up has occurred. Refer to product data sheet for instructions.
Remove all dust and wipe down with a turpentine moistened cloth.
Apply a primer coat of undiluted BRICKDRESSING. Allow 12 hours drying.

GOOD CONDITION

Sandpaper lightly with 100 grit sandpaper. Wipe down with a turpentine moistened cloth.

FINAL COATS

Apply two coats BRICKDRESSING as supplied, allowing 12 hours drying time between coats.

DISCLAIMER

The technical information contained in this document are given in good faith and are meant to be used as a guideline by the specifier or user. Whilst we are confident about the quality of our products, we cannot accept any liability for the incorrect use or application of our products. Surface preparation forms an integral part of the scope of works and it is expected that the highest standards are maintained during surface preparation and application, to ensure that our products perform as intended. Always ensure to use the same product batch numbers, refrain from doing spot touch-ups and paint surfaces from corner to corner to prevent colour and sheen variance.

Please note that all our latest Product Data Sheets and Material Safety Data Sheets are available for viewing on our website at www.sabre.co.za

SABRE PAINTS (PTY) LIMITED